



**Installation Methods:** Parquet, Herringbone, Basketweave, Ashlar

### Product Specifications

<b>Construction</b>	Textured Loop
<b>Backing</b>	Nexus® Modular
<b>Dye Method</b>	Solution Dyed
<b>Fiber Type</b>	Encore® SD Ultima® (with recycled content)
<b>Face Weight</b>	18 oz./sy (610 grams/m2)
<b>Pile Density</b>	10800 oz./y3 (400.47 kg/m3)
<b>Pattern Repeat</b>	N/A
<b>Gauge</b>	1/10 (3.94 rows/cm)
<b>Stitches Per Inch</b>	10.26 stitches/in (4.04 stitches/cm)
<b>Standard Size</b>	12" x 48" approx. (30.48cm x 121.92cm)
<b>Standard Adhesive</b>	Commercialon Premium Modular and LVT Adhesive
<b>Optional Adhesive</b>	TileTabs
<b>Standard Warranties</b>	<b>Nexus Modular</b> <b>Commercialon Adhesive for Modular Carpet &amp; LVT</b> <b>Nexus FC Cushion</b> <b>Encore SD Ultima Fiber</b>
<b>Optional Warranties</b>	<b>Commercialon High Moisture Adhesive for Modular Carpet and LVT</b> <b>Advance Modular Backing</b> <b>Tile Tabs</b> <b>Encore® 100 Fiber</b>

### Special Technologies

<b>ProSept® Antimicrobial</b>	Optional
<b>ProTex® Soil Release</b>	Standard
<b>Sentir® Odor-Blocker</b>	Optional

### Environmental Specifications & Tests

<b>NSF 140:</b>	Gold Certified
<b>Total Recycled Content</b>	45.8%
<b>Radiant Panel</b>	Class 1
<b>Smoke Density</b>	Less than 450 flaming (ASTM E 662)
<b>Static Test</b>	Less than 3 kv (AATCC-134)
<b>ADA Compliance</b>	Compliant For Accessible Routes
<b>Pill Test</b>	Yes
<b>Lightfastness</b>	Yes

### Colorways



CMT14 Golden Intui...



CMT38 Teal Harm...



CMT47 Sage Affinity



CMT49 Indigo Spirit



CMT51 Pewter Ra...



CMT56 Platinum B..



CMT58 Graphite Li...



CMT75 Mink Esse...



CMT76 Bark Integ...



CMT77 Obsidian M..



CMT98 Plum Conc...